

2

(NASA-CR-130063) THE SYNERGISTIC EFFECTS
OF SLIP RING-BRUSH DESIGN AND MATERIALS
Interim Report, Dec. - Mar. 1972 N.E.
Lewis, et al (Poly-Scientific Div.) May
1972 29 p
N72-32230
Unclas
CSCL 09A G3/09 43355

THE SYNERGISTIC EFFECTS OF SLIP RING-BRUSH DESIGN AND MATERIALS

N. E. Lewis, and E.W. Glossbrenner
Poly-Scientific Division
Litton Systems, Inc.
1213 North Main Street
Blacksburg, Virginia 24060

May 1972

Interim Report for Period December - March 1972

Prepared for
GODDARD SPACE FLIGHT CENTER
Greenbelt, Maryland 20771

Reproduced by
NATIONAL TECHNICAL
INFORMATION SERVICE
U.S. Department of Commerce
Springfield VA 22151

1. Report No. 2. Govt. Accession No.		3. Recipients Catalog No.	
4. Title and Subtitle The Synergistic Effects of Slip Ring-Brush Design and Materials		5. Report Date May 1972	
7. Author(s) N.E. Lewis and E.W. Glossbrenner		6. Performing Organization Code	
		8. Performing Organization Report No.	
9. Performing Organization Name and Address Poly-Scientific Division Litton Systems, Inc. 1213 North Main Street Blacksburg, Virginia 24060		10. Work Unit No.	
		11. Contract or Grant No. NAS 5-21146	
12. Sponsoring Agency Name & Address Goddard Space Flight Center Greenbelt, Maryland 20771 Technical Officer: Charles E. Vest Code 764		13. Type of Report and Period Interim Report for Period December - March 1972	
		14. Sponsoring Agency Code	
15. Supplementary Notes			
16. Abstract This program has involved the design, fabrication and subsequent testing of four power slip rings for synchronous orbit application. Environmental and instrumentation systems necessary for monitoring electrical noise, friction and brush wear in air and at less than 5×10^{-8} torr have been developed. Composite brushes consisting of silver-molybdenum disulfide-graphite and silver-niobium diselenide-graphite have been employed on rings of coin silver and rhodium plate. These four contact combinations have been tested during an ambient condition run-in at 150 RPM and a humidity sequence at 0.1 RPM. At this time the first nine months of a two year vacuum test being performed at 0.1 RPM have been completed.			
17. Key Words Friction, Wear, Electrical Noise Composite Lubricants		18. Distribution Statement	
19. Security Classif. (of this report)	20. Security Classif. (of this report)	21. No. of Pages	22. Price

PREFACE

This program involves the design, fabrication and subsequent testing of four power slip rings for synchronous orbit application. Frequent and simultaneous recording of friction, wear and electrical noise enable the synergistic effects of contact materials and slip ring-brush design to be studied.

The four ring and brush material combinations under evaluation are as follows:

- (A) Poly-Scientific ES383 brushes vs rings of rhodium plate over nickel plate on a brass substrate (Combination A)
- (B) Poly-Scientific ES383 brushes vs coin silver (silver - 10% copper) rings (Combination B)
- (C) Poly-Scientific ES384 brushes vs rings of rhodium plate over nickel plate on a brass substrate (Combination C)
- (D) Poly-Scientific ES384 brushes vs coin silver rings (Combination D)

These four contact combination have been tested under the following conditions:

1. Run-in at 150 RPM for 10 hours.
2. A five day humidity sequence at 0.1 RPM.
3. Nine months of vacuum operation ($<5 \times 10^{-8}$ torr) at 0.1 RPM.

The results of the run-in, humidity and first six months of vacuum operation have been previously reported.⁽¹⁹⁻²⁰⁾ Portions of these reports have been repeated here to maintain continuity. Conclusions based on the last three months of vacuum data are not being drawn in this report. The conclusions previously drawn after six months of vacuum operation were as follows:

Electrical Noise

1. A significant difference between inductive vs resistive loading does not appear to exist.

2. Noise levels across the positive brushes were found to be significantly lower than those across the negative brushes.
3. Coin silver ring material gave better results than rhodium plate.
4. Brushes lubricated with MoS_2 gave lower noise values than those lubricated with NbSe_2 .
5. The Ag- MoS_2 -C/Ag combination gave the better performance than the other three combinations.

Friction

1. All combinations showed a significant decrease in friction in going from air operation to vacuum operation.
2. Those brushes lubricated with MoS_2 gave lower coefficients of friction in vacuum than those lubricated with NbSe_2 .

Wear

1. The Ag- NbSe_2 -C/Ag combination has yielded the lowest total wear and wear rate throughout vacuum operation to date.
2. Based on total wear, the Ag- MoS_2 -C/Rh, Ag- MoS_2 -C/Ag and Ag- NbSe_2 -C/Rh combinations have yielded equivalent wear rates.
3. After 1000 hours of vacuum operation the Ag- MoS_2 -C/Ag and Ag- NbSe_2 -C/Rh combinations appear to be wearing at the highest rates.
4. Projecting from the 1000-4300 hours vacuum data, it would appear that low rate is the result of combination performance rather than a particular ring or brush material.

It is recommended that the two year vacuum test continue and data be collected at a frequency of twice per week.

TABLE OF CONTENTS

<u>Section</u>	<u>Title</u>	<u>Page</u>
	PREFACE.....	iii
I	INTRODUCTION.....	1
II	EXPERIMENTAL.....	3
III	DATA COLLECTION.....	4
IV	DISCUSSION.....	6
	A. Electrical Noise.....	6
	B. Friction.....	6
	C. Wear.....	6
V	NEW TECHNOLOGY.....	12
VI	PROGRAM FOR NEXT REPORTING PERIOD.....	13
VII	CONCLUSIONS.....	14
VIII	RECOMMENDATIONS.....	16

LIST OF FIGURES

<u>Figure</u>	<u>Title</u>	<u>Page</u>
1	Electrical Noise, Friction and Wear During.... Vacuum Operation At 0.1 RPM	8

LIST OF TABLES

<u>Table</u>	<u>Title</u>	<u>Page</u>
1	Data Collection Frequency.....	5
2	Statistical Analysis of the Means of the.... Electrical Noise Data.....	7
3	Average Electrical Noise Levels.....	9
4	Friction Coefficients.....	10

THE SYNERGISTIC EFFECTS OF SLIP RING-BRUSH DESIGN AND MATERIALS

BY

N. E. LEWIS

AND

E. W. GLOSSBRENNER

POLY-SCIENTIFIC DIVISION

LITTON SYSTEMS, INC.

I. INTRODUCTION

Increasing satellite complexity, power usage and long life requirements are demanding more precise knowledge of sliding contact performance in the vacuum of outer space. Applications of slip rings for exceptionally long life have traditionally been dependent upon the use of contacts with solid lubricants of lamellar structure. With space missions now being projected to 10 years and longer and with more complex optical systems the selection of this type construction is nearly mandatory. This type of contact is being considered for transmission of high power levels from the solar array to the vehicle of future satellites and space stations in synchronous orbit. Such arrays rotate at the average speed of one revolution per day to maintain relative alignment to the sun and to earth stations. Such slow speeds might, it was thought, severely limit the performance of sliding contact power transfer devices.

Previous studies(1-18) have explored the performance of various contact materials in the vacuum environment. Most of these have been in relative high pressure $\approx 10^{-6}$ torr or were operated with high surface speeds to accelerate performance patterns of the contact materials.

This paper presents the results of four contact material combinations operated with a current density of 100 A/in² at speeds simulating

earth rate rotation and low pressure similar to synchronous orbit vacuum. Silver graphite composite brushes utilizing equal volume fractions of MoS_2 or NbSe_2 lubricants were employed with rings of coin silver and rhodium plate. Emphasis has been placed on instrumentation and systems design to permit periodic monitoring of friction, wear and electrical noise. Data from brief air tests and nine months of vacuum operation have been presented.

II. Experimental

The equipment, instrumentation, techniques and materials analysis employed to date have been previously reported.¹⁹ There have been no changes since that reporting.

III. Data Collection

Friction, electrical noise and wear measurements were taken from the four materials combinations during the following three periods:

1. Ten hours of run-in with a ring speed of 150 RPM.
2. Five days at controlled humidity, changing from 30-40% RH to 70-80% RH every 24 hours with a ring speed of 0.1 RPM.
3. Nine months at a pressure of $<5 \times 10^{-8}$ torr with a speed of 0.1 RPM.

Table I gives the number of data recordings for each of the three parameters during the three test periods.

Each time data was collected during the run-in period, the measurements were recorded over a time interval representing 15-20 ring revolution, under conditions of controlled humidity and vacuum.

The electrical noise data represent the maximum peak to peak (P-P) value recorded during each data collection interval (Tables 2 and 3 and Figure 1). The friction coefficients were determined using the maximum tangential force recorded during each interval (Table 4 and Figure 1). The variation in brush displacement with time under vacuum has been shown in Figure 1.

Future reference to the four brush and ring combinations will be as follows:

- (A) Ag-MoS₂-C brushes on Rh rings (Combination A)
- (B) Ag-MoS₂-C brushes on Ag rings (Combination B)
- (C) Ag-NbSe₂-C brushes on Rh rings (Combination C)
- (D) Ag-NbSe₂-C brushes on Ag rings (Combination D).

TABLE 1
DATA COLLECTION FREQUENCY

Test Period	Number of Recordings Materials Combinations			
Run-In Ambient	A Ag-MoS ₂ -Rh	B Ag-MoS ₂ -C/Ag	C Ag-NbSe ₂ -C/Rh	D Ag-NbSe ₂ -C/Ag
Condition 0-10 Hrs.	8	3	2	2
Relative Humidity 30-40% 70-80% 0-24 Hrs.	3	3	3	3
24-48 Hrs.	3	3	3	3
48-72 Hrs.	3	3	3	3
72-96 Hrs.	3	3	3	3
96-120 Hrs.	3	3	3	3
Vacuum 0-10 Hrs.	7	7	7	7
10-32 Hrs.	6	6	6	6
32-100 Hrs.	8	8	8	8
100-1000 Hrs.	38	38	38*	38
1000-4300 Hrs.	26	26	26	26
4300-7700 Hrs.	21	21	21	17**

*After 1000 Hours 4 of 6 circuits were not operational.

**Feedthrough bearings failed after 7056 hours.

IV. Discussion

The run-in, humidity and first six months of vacuum data were treated in a previous report⁽²⁰⁾. Only the Tables and Figures necessary to maintain continuity of the vacuum data are being repeated in this report.

A. Electrical Noise

A statistical analysis of the data was conducted after six months of vacuum operation. The results of that study have been repeated in Table 2. A similar statistical analysis will not be repeated until more data have been generated. It was concluded from that analysis that a significant difference between inductive and resistive loading for all combination did not exist. For this reason and for sake of clarity the inductive and resistive electrical noise data have been averaged in Figure 1. The additional three months of vacuum data do not appear to have made any significant difference from the first six months of data (Figure 1 and Table 3).

B. Friction

After the completion of six months of vacuum operation, the MoS₂ lubricated brushes were yielding lower coefficients of friction (0.12) than those lubricated with NbSe₂ (0.29). During the last three months of vacuum operation the MoS₂ lubricated brushes have moved up to a level of 0.25 while the NbSe₂ lubricated ones have remained nearly constant at 0.31.

C. Wear

The last three months of vacuum data have confirmed the projections made after six months of operation. At that point it appeared that the Ag-MoS₂-C/Ag and Ag-NbSe₂-C/Rh combinations were wearing at the highest rates. The wear data in Figure 1 indicates these combinations are wearing at a higher rate than the Ag-MoS₂-C/Rh and Ag-NbSe₂-C/Ag combinations. As previously concluded, it appears that wear performance is a result of materials combination rather than a single ring or brush material.

TABLE 2
STATISTICAL ANALYSIS OF THE MEANS OF THE ELECTRICAL NOISE DATA

Parameter Analyzed	TEST CONDITION							
	Run-In 0-10 Hrs.		Humidity 0-120 Hrs.		0-100 Hrs.		100-4300 Hrs.	
	TEST	CL*	TEST	CL*	TEST	CL*	TEST	CL*
Electrical Load Differences	$A_L = A_R$ $B_L = B_R$ $C_L = C_R$ $D_L < D_R$ 60		$A_L < A_R$ 83.5 $B_L < B_R$ 99.9+ $C_L < C_R$ 99.9+ $D_L = D_R$		$A_L < A_R$ 99.9+ $B_L = B_R$ $C_R < C_L$ 96.7 $D_R < D_L$ 97.6		$A_L < A_R$ 99.3 $B_L < B_R$ 99.9+ $C_R < C_L$ 99.9+ $D_L < D_R$ 99.9+	
Polarity Differences	$A_R^+ < A_R^-$ 99.9 $B_R^+ = B_R^-$ $C_R^+ < C_R^{**}$ $D_R^+ < D_R^{**}$		$A_R^+ < A_R^-$ 99.9+ $B_R^- < B_R^+$ 99.9+ $C_R^+ < C_R^-$ 99.9+ $D_R^+ < D_R^-$ 82.7		$A_R^+ < A_R^-$ 99.9+ $B_R^+ < B_R^-$ 99.9 $C_R^+ < C_R^-$ 99.9 $D_R^+ < D_R^-$ 99.9		$A_R^+ < A_R^-$ 99.9+ $B_R^- < B_R^+$ 99.9+ $C_R^+ < C_R^-$ 99.9+ $D_R^+ < D_R^-$ 99.9+	
Ring Material Differences	$B_R < A_R$ 99.9+ $B_L < A_L$ 99.9+ $C_R < D_R$ 80 $C_L = D_L$		$B_R < A_R$ 99.9+ $B_L < A_L$ 99.9+ $D_R < C_R$ 99.9+ $D_L < C_L$ 99.9+		$B_R < A_R$ 99.9+ $B_L < A_L$ 77.8 $D_R < C_R$ 99.9+ $D_L < C_L$ 99.9+		$A_R < B_R$ 98 $B_L < A_L$ 99.8+ $D_R < C_R$ 99.9+ $D_L < C_L$ 99.9+	
Brush Material Differences	$C_R < A_R$ 99.9+ $C_L < A_L$ 99 $B_R < D_R$ 97 $B_L < D_L$ 76		$A_R < C_R$ 99.9+ $A_L < C_L$ 99.9+ $B_R < D_R$ 88.9 $B_L < D_L$ 99.9+		$A_R < C_R$ 99.9+ $A_L < C_L$ 99.9+ $D_R < B_R$ 99.9+ $B_L = D_L$		$A_R < C_R$ 99.9+ $A_L < C_L$ 99.9+ $B_R < D_R$ 99.9+ $B_L < D_L$ 99.9+	
Material Combination Differences	$D_R < A_R$ 92.6 $B_R = C_R$ $D_L < A_L$ 99 $B_L < C_L$ 60		$D_R < A_R$ 99.9+ $B_R < C_R$ 99.9+ $D_L < A_L$ 99.9+ $B_L < C_L$ 99.9+		$D_R < A_R$ 99.9+ $B_R < C_R$ 99.9+ $D_L < A_L$ 97.6 $B_L < C_L$ 99.9+		$A_R < D_R$ 99.9+ $B_R < C_R$ 99.9+ $A_L < D_L$ 99.9+ $B_L < C_L$ 99.9+	

A - Ag-MoS₂-C/Rh

B - Ag-MoS₂-C/Ag

C - Ag-NbSe₂-C/Rh

D - Ag-NbSe₂-C/Ag

\pm denote brush polarity.

L and R denote inductive or resistive load respectively

*Confidence limits are for two tailed testing

H₀: X = Y H_a: X \neq Y

**Two observations only.




FIGURE 1. ELECTRICAL NOISE, FRICTION AND WEAR DURING VACUUM OPERATION AT 0.1 RPM

TABLE 3

AVERAGE ELECTRICAL NOISE LEVELS

Test Period	Run-In		Humidity		Vacuum		
	0 Hrs.	10 Hrs.	0 Hrs.	120 Hrs.	0 Hrs.	100 Hrs.	7700 Hrs.
(A) Ag-MoS ₂ -C/Rh	21.8	35.8	33.7	45.3	57.8	28.5	4.5
(B) Ag-MoS ₂ -C/Ag	6.6	9.5	12.8	15.7	23.5	13.5	12.7
(C) Ag-NbSe ₂ -C/Rh	5.3	15.2	31.0	100.8	71.5	50.2	61.0
(D) Ag-NbSe ₂ -C/Ag	19.8	10.8	13.8	21.0	18.2	13.3	31.5

*Average includes both resistive and inductive circuits.

TABLE 4
FRICTION COEFFICIENTS

<u>Test Period</u>	Run-In		Humidity		Vacuum	
	<u>Initial</u>	<u>Final</u>	<u>Initial</u>	<u>Final</u>	<u>Initial</u>	<u>Final</u>
(A) Ag-MoS ₂ -C/Rh	0.43	0.32	0.17	0.25	0.26	0.22
(B) Ag-MoS ₂ -C/Ag	0.41	.55*	0.44	0.46	0.30	0.30
(C) Ag-NbSe ₂ -C/Rh	0.33	0.57	0.48	0.37	0.40	0.25
(D) Ag-NbSe ₂ -C/Ag	0.41	0.38	0.33	0.48	0.54	0.36

*Average of three brushes.

As a result of feedthrough bearing failure after approximately 7000 hours of vacuum operation, rotation on combination D has ceased. Power is being kept on the fixture so cold welding tests can be performed at a later date.

V. NEW TECHNOLOGY

The system, experimental techniques and results reported to date do not directly represent a form of new technology.

VI. PROGRAM FOR NEXT REPORTING PERIOD

During the next reporting period the vacuum test will continue. Data will be taken on a twice per week basis.

VII. CONCLUSIONS

At this point, nine months of vacuum operation have been concluded. The results generated during the last three months of operation have not significantly altered the conclusions drawn after six months of operation. The conclusions drawn at that time were as follows:

A. Electrical Noise

1. A significant difference between inductive vs. resistive loading did not appear to exist.
2. Noise levels across the positive brushes were found to be significantly lower than those across the negative brushes.
3. Coin silver ring material gave better results than rhodium plate.
4. Brushes lubricated with MoS_2 gave lower noise values than those lubricated with NbSe_2 .
5. The $\text{Ag-MoS}_2\text{-C/Ag}$ combination gave better performance than the other three combinations.

B. Friction

1. All combinations showed a significant decrease in friction in going from air operation to vacuum operation.
2. Those brushes lubricated with MoS_2 gave lower coefficients of friction in vacuum than those lubricated with NbSe_2 .

C. Wear

1. The $\text{Ag-NbSe}_2\text{-C/Ag}$ combination yielded the lowest total wear and wear rate throughout vacuum operation to date.
2. Based on total wear, the $\text{Ag-MoS}_2\text{-C/Rh}$, $\text{Ag-MoS}_2\text{-C/Ag}$ and $\text{Ag-NbSe}_2\text{-C/Rh}$ combinations have yielded equivalent wear rates.
3. After 1000 hours of vacuum operation the $\text{Ag-MoS}_2\text{-C/Ag}$ and $\text{Ag-NbSe}_2\text{-C/Rh}$ combinations appear to be wearing at the highest rates.

4. Projecting from the 1000-4300 hours vacuum data, low wear rate is the result of combination performance rather than a particular ring or brush material.

VIII. RECOMMENDATIONS

This program should continue with the data collection frequency of twice per week until the completion of two years at less than 5×10^{-8} torr. At that time a post test analysis should be performed, the parts refurbished and the four-month test at speeds of 0.1 and 4 RPM should be completed.

REFERENCES

1. Adkins, R. L. "Performance Test of Power Transmission on Slip Rings in Vacuum Environments" Aerospace Environmental Facility Prepared under Contract AF 30(600)-100, November 1964.
2. Boes, D. J. and P. H. Bowen, "Friction Wear Characteristics of Self-Lubricating Composites Developed for Vacuum Service" ASLE Transactions, Vol. 6 (1963, pp. 192-200).
3. Buckley, Donald H., Max Swikert and Rober L. Johnson, "Friction, Wear and Evaporation Rate of Various Materials in Vacuum to 10^{-7} mm Hg" ASLE Transactions, Vol 5 (1962), pp. 8-23.
4. Clauss, Francis J., "Lubrication of Ball Bearings and Slip Rings under High Vacuum" Lockheed Missile and Space Company (N64-19952, pp. 41-76).
5. Clauss, Francis J., "Long Lived Lubrication for Spacecraft Equipment Present at Air Transport Space Meeting" New York, New York, April 21-30, 1964 (Sponsored by SAE-ASME)(A64-20633).
8. Clauss, Francis J., C.F. O'Hara and W. O. Kassenbaum "Behavior of Slip Rings in Space Environment" Lockheed Missiles and Space Division, 1962 (AD 4169345).
9. Cunningham, A.C. "Long Life Slip Rings for Vacuum Operation" Proceedings 16th Annual Holm Seminar on Electrical Contact Phenomena, pp. 73-97, November 1971.
10. Demorest, K. E. and A. F. Whitaker "Evaluation of Direct Current Motors in Vacuum" NASA TM X-53675, November 24, 1967.

11. Harris, C. L. and D. Wyn-Roberts "Friction and Wear Studies in Ultra High Vacuum and the Evaluation of Electrical Slip Rings" AD69-18561.
12. Jones, J. R. "Friction and Wear Tests of Potentiometer Contacts in Vacuum" (Final Report on JPL 950056) Hughes Aircraft Company.
13. Marason, G. and K. Zimmerman "Slip Rings for High Vacuum Operation" Proceedings of the Third International Research Symposium on Electrical Contact Phenomena, University of Maine, June 1966, p. 179.
14. Moberly, L. E. and J. L. Johnston "Electrical Sliding Contacts for Application in Space Environments" Supplement to IEEE Transactions on Aerospace, June 1965, pp. 252-257.
15. Murray, S. R. and H. E. Marx "Evaluation of Slip Rings for Spatial Applications" General Electric Company, Schenectady, N.Y. Report No. 61GL85, March 1961.
16. "Report on the Vacuum Evaluation of Slip Rings and Brushes for Space Applications" Elliott Brothers (London) Limited Space and Weapons Research Laboratory Camberley, Surrey, March 1968. Prepared for ESRO under ESTEC Contract No. 416/67SL (N69-24270).
17. Ulrich, Donald "An Analysis of the Variation in Wear Life of Hot Pressed Molybdenum Disulfide Silver Electrical Contact Brushes in Vacuum" NASA Technical Memorandum, NASA TMX-53146, October 5, 1964.
18. Pentlecki, C. J. and Glossbrenner, E. W. "The Testing of Contact Material for Slip Rings and Brushes for Space Application" Proceedings 17 Annual Holm Seminar on Electrical

Contact Phenomena pp. 157-172, November 1971.

19. Lewis, Cole, Glossbrenner "The Synergistic Effects of Slip Ring-Brush Design and Materials" Interim Report for Period March-June 1971.
20. Lewis, N. E. and Glossbrenner, E. W. "The Synergistic Effects of Slip Ring-Brush Design and Materials" Interim Report for Period September-December 1971.